



Product Information Sheet



Sheet Number: **0034**

Rev 22-11-06

Stencilshield Aggregate Base Polymer Enhanced Cement Trowel On Base

Aggregate Base is a polymer enhanced pre-mixed cement render suitable for base coating Aggregate Concrete to give a smooth base in preparation for Stencilshield coatings. It is sold in 20 kg bags. We recommend the addition of 500mls of Concrebond to each bag to increase adhesion and make it more crack resistant.

General Application Guide:

- After 48 hrs, Stencilshield Base Coat can be applied in a chosen colour.
- Then layout a pattern with stencil or tape.
- Then apply 2 coats of Stencilshield Top Coat.
- The next day remove the tape or stencil pattern and apply 1 coat of Covercoat W sealer.

Please use application guides such as Stencilshield Top/Base for more detailed information regarding application.

Specifications:

(all dry times are considered at 25° C and at 50% humidity)

Surface Dry: 4 -5 hours

Top Coat: 48 hours min.

Hard Dry: 4 -5 days

Full Cure: 28 days

Wet Film Thickness: N/A

Dry Film Thickness: N/A

Thinning: Mix with approximately 3 litre of water per 20 kg bag and 500 mls of Concrebond

Clean Up: Clean up with water

Features:

Simple to mix



Easy to coat when dry



Some Flexibility



Easy To Apply



Medium to High Build Finish



Pre Mixed



Cost effective



Benefits:

Just use an electric drill mixer



Can be painted



Allows for some substrate move-



Trowel



1 coat at 3-6mm



Accurate mixes



More competitive for applicator



Notes: There are many substrates on the market. Please consult Shieldcoast for further information regarding applications not on this sheet.

See MSDS for safety information