



Product Information Sheet



Sheet Number: **0034**

Rev 18-05-2010



Aggregate Base Polymer Enhanced Cement Trowel On Base

Features:

Aggregate Base is a polymer enhanced pre-mixed cement render suitable for base coating Aggregate Concrete to give a smooth base in preparation for Stencilshield coatings. It is sold in a 20 kg bags. We recommend mixing to smooth paste approximately 1lt of Concrebond and 2 to 3 lts of water to each bag to increase adhesion and make it more crack resistant.



General Application Guide:

- Trowel or squeegee on Aggregate-base mix
- After 48 hrs, Stencilshield Base Coat can be applied in a chosen colour.
- Then layout a pattern with stencil or tape.
- Then apply 2 coats of Stencilshield Top Coat.
- The next day remove the tape or stencil pattern and when completely dry apply 1 thin coat of Covercoat W sealer with and airless sprayer or Concreshield X with a roller.

Specifications:

(all dry times are considered at 25° C and at 50% humidity)

Surface Dry: 4 -5 hours

Top Coat: 48 hours min.

Hard Dry: 4 -5 days

Full Cure: 28 days

Wet Film Thickness: N/A

Dry Film Thickness: N/A

Clean Up: Clean up with water

Notes:

Please use application guides such as Stencilshield Top/Base for more detailed information regarding application.

- Simple to mix
- Easy to coat when dry
- Some Flexibility
- Easy To Apply
- Medium to High Build Finish
- Easy Mixed
- Cost effective

Benefits:

- Just use an electric drill mixer
- Can be painted
- Allows for some substrate move-
- Troweled
- 1 coat at 3-6mm
- Environmentally friendly
- More competitive for applicator



See MSDS for safety information

Shieldcoat has become one of the first paint manufacturer in Australia to meet the international environmental standard, ISO 14001

